



## **Technical specifications**

Fabscrap meets the requirements of EN-ISO 10581

	Binder content	EN ISO 10581	type 1
	Total thickness	EN ISO 24346	2.0 mm
	Surface finish		SMART top
	Collection size		4
iii)	Commercial use	EN ISO 10874	34 very heavy
iii.	Light industrial use	EN ISO 10874	43 heavy
	Roll width	EN ISO 24341	2 m
	Roll length	EN ISO 24341	≤ 27 m ~ 26 m
	Total weight	EN ISO 23997	2.9 kg/m²
K A	Dimensional stability	EN ISO 23999	≤ 0.2 %
	Residual indentation Typical value	EN ISO 24343-1	≤ 0.10 mm - 0.03 mm
	Abrasion resistance	EN 660-2	group T
	Castor chair continuous use	ISO 4918 / EN 425	pass
<b>**</b>	Light fastness	ISO 105-B02	≥7
2	Flexibility	EN ISO 24344	0 10 mm
	Resistance to chemicals	EN ISO 26987	very good
	Slip resistance	DIN 51130	R9
	Wetroom application	EN 13553	yes
<b>*</b>	Bacteria resistance	EN 846	Does not support growth
,	Fabscrap meets the requirements of EN 14041		D1.140.01 C € 0200001-0-9-9-0
	Indoor Air Emissions: TVOC after 28 days	ISO 16516	≤ 0.01 mg/m³
B <sub>2</sub> -51	Reaction to fire	EN 13501-1	B <sub>e</sub> -s1, L, NCS
T DS	Slip resistance	EN 13893	µ ≥ 0.30
7	Body voltage	EN 1815	≤ 2 kV
	Thermal conductivity	EN 12524	0.25 W/m-K
	Content of specific dangerous substances	EN 14041	Compliant, not actively added



